

UltraTack transparent ASLAN DFP 06

Transparent digital printing film with extra strong adhesion for difficult surfaces

With extra strong adhesion, this transparent, polymeric softened digital printing film is perfect for long-term applications requiring rock-solid, permanent adhesion. The silicone paper liner, PE-coated on both sides, provides high resistance to moisture and heat and guarantees optimum printing results.

Thanks to the film's transparency, even hard-to-stick surfaces can be designed with sharply defined, cut-out motifs, without time-consuming plotting. Incorporating very detailed graphics, fade-out colour gradients or the look of the surface into the design also becomes possible with this strongly adhesive film for almost any substrate.

To significantly extend the life of your prints, we recommend our PremiumProtect ASLAN SL 17 and PremiumProtect Matt ASLAN SL 18 laminates. They are ideal for use with the UltraTack range and offer protection from UV-rays, the weather and mechanical wear.

For further information or questions regarding special applications please contact our technical advisory service:
+49 2204.708-80

Construction

| | | |
|----------------|--|--|
| face-film: | PVC, polymeric softened, transparent, glossy | |
| thickness: | ~ 80 µm | |
| adhesive: | pressure sensitive polyacrylate adhesive | square quantity: ~ 35 g/m ² |
| release liner: | silicone paper, PE-coated on both sides | square weight: ~ 140 g/m ² |

Characteristics

| | | |
|-----------------------------------|--|-------------------------------------|
| adhesive strength: (ASTMD-903) | applied on stainless steel immediately after 1 week | ~ 12.5 N/25 mm ~ 22 N/25 mm |
| dimensional stability: | applied onto aluminum after 48 hours stored at 70 °C (25 x 25 cm) | max. -0.45 % |
| chemical resistance: | In a preece test of 24 hours the applied film is resistant to most petroleum based oils, greases and aliphatic solvents, mild acids, alkaline and salts. | |
| light proofness: | DIN 53 388 | non-fade grade: 7-8 (wool-scale) |
| combustibility: | Stuck on aluminum, the film is self-extinguishing. | |
| temperature: | application temperature: service temperature range: | min. 5 °C -30 °C up to +80 °C |
| durability: | up to 7 years outdoors, with vertical exposure, in central European standard climatic conditions | |

ASLAN, Schwarz GmbH & Co. KG

Oberauel 2 · 51491 Overath · Germany

phone +49(0)2204.708 80 · fax +49(0)2204.708 50

e-mail info@ASLAN-Schwarz.com



www.ASLAN-Schwarz.com

ASLAN®

EXPERTISE IN SELF-ADHESIVE FILMS

UltraTack transparent ASLAN DFP 06

Processing

| | |
|----------------------|---|
| printability: | The material is printable with solvent, eco-solvent, UV-curable and latex inks as well as with screen printing inks. In case of inadequate drying of the print-inks the film will be sodded and the adhesive negatively affected. |
| application: | <p>Application dry or wet. If applied wet, a whitening of the adhesive can occur, but will disappear after a couple of days depending on the weather conditions.</p> <p>We recommend to perform a test application before applying the film onto surfaces with a non-stick coating such as box bodies for trailers, which are made out of plywood material, or plastic waste bins.</p> <p>For wet applications we recommend the transfer liquid ASLAN TL10. For the application of lettering etc. we recommend our ASLAN application tapes, respectively the ASLAN TMO.</p> |
| gloss: | There can be matt areas on the surface of the highly glossy film near the core of the roll. These can be caused by the rear of the backing paper, but will disappear after a short period of time and do not influence the print results. |
| storage life: | Before application, the films can be stored for minimum 2 years from date of production. The film must be stored at room temperature (15-25 °C) and a relative humidity of the air of 50-60 %. To avoid pressure points appearing on the roll surface, we recommend the rolls be stored either standing vertical or on `hanging´ racks designed for this purpose. |

State: 02|2018

All technical data and advice is based on our experience and measured testing that we believe to be reliable. It remains the customer's responsibility to test the suitability of our products for the intended purpose.

The quality of our products is regularly examined, upgraded and developed. We take the right, without prior notice, to adjust, upgrade and improve the chemical structures or physical characteristics of our products in accordance with our latest knowledge.

ASLAN, Schwarz GmbH & Co. KG

Oberauel 2 · 51491 Overath · Germany

phone +49(0)2204.708 80 · **fax** +49(0)2204.708 50

e-mail info@ASLAN-Schwarz.com



www.ASLAN-Schwarz.com

ASLAN®
EXPERTISE IN SELF-ADHESIVE FILMS