

PRODUCT DESCRIPTION

BF PRINTUV is a polyurethane printable film, made specifically for UV inks.

It's free of PVC, plasticizers and heavy metals.

The adhesive line guarantees ease of work during all phases, including printing and weeding. After cutting and weeding BF PRINT UV, it can be positioned on the garment using BF MYLAR, which will then be removed hot.

Due to the nature of UV inks, you can cut BF PRINTUV and apply it immediately after printing, without having to wait for the inks to dry.

APPLICATION INSTRUCTIONS

- Print your design directly on BF PRINTUV, without mirroring.
- Cut BF PRINTUV using a 45° blade.
- Weed BF PRINTUV and remove the excess material.
- Apply BF MYLAR on the printed design, being careful not to create any air bubbles.
- Remove the design for its liner.
- Set your press to 140°C / 285°F
- Place your garment and the press and center your design.
- Press at 140°C / 285°F for 10 seconds
- Remove BF MYLAR while hot

STANDARD SIZES

- H 150 cm => Available lengths:
25 mt (upon request)
- H 100 cm => Available lengths :
25 mt (upon request)
- H 75 cm => Available lengths :
25 mt (upon request)
- H 50 cm => Available lengths :
25 mt / 12,5 mt (standard)

SUGGESTED APPLICATIONS

- Reccomended fabrics: cotton, synthetics, mixed
- Cut designs as small as 0.5cm

TECHNICAL DATA

Film:	PU/ polyurethane
Thickness:	80 μ (±5%)
Carrier:	Lightly adhesive PET

APPLICATION

Temperature:	140°C - 285° F
Time:	10"
Pressure:	medium / 3,5 bar – 50 PSI

LINER REMOVAL

While hot

WASH RESISTANCE

First wash:	12 hours after application
Max Temperature:	60° C
Dry clean:	NO
Softener:	NO
Bleach:	NO
Dryer:	NO

SAFETY DATA SHEET

The data represent the average values tested in our laboratory at normal environmental conditions. This information is given without guarantee.

Due to variances in the manufacturing process of fabric, B-Flex Italia S.r.l. highly recommends conducting a test on the desired material before each application.

This technical data sheet is to be considered valid for the following products: BF PRINTUV. Rev_20 / 10.