

# Interlam™

## Pro Emerytex®

Interlam™ Pro Emerytex® is a 4 mil (100µ) monomeric soft calendared PVC laminating film with a matte pebble textured finish, coated on one side with a pressure sensitive acrylic adhesive that is protected by a bleached Kraft release paper coated on both sides with PE and siliconised on the release side. Both the film and adhesive contain UV stabilisers, which protect against UV degradation. The anti-slip properties of Interlam™ Pro Emerytex® have been tested in accordance with DIN 51130 standards and have been awarded an R11 rating.

- RECOMMENDED FOR LAMINATING MOUNTED PRINTS THAT WILL BE PLACED IN HIGH TRAFFIC INDOOR AND OUTDOOR DISPLAY AREAS
- IDEAL FOR TRADESHOW GRAPHICS, POP DISPLAYS, MOUSE PADS, COUNTER MATS, EVENT SIGNAGE, FLOOR GRAPHICS, AND OTHER SIGNAGE WHERE A SCUFF-RESISTANT FINISH IS REQUIRED
- INTERLAM™ PRO EMERYTEX® HAS A CLASS 0 FIRE RATING ACCORDING TO UK STANDARDS FOR SURFACE SPREAD OF FLAME, MAKING IT PERFECT FOR APPLICATIONS IN PUBLIC AREAS THAT REQUIRE COMPLIANCE WITH STRICT FIRE REGULATIONS, SUCH AS AIRPORTS, HOTELS AND HOSPITALS
- CAN BE COMBINED WITH DRYTAC'S FLOORTAC™ PRINT MEDIA TO CREATE A SLIP-RESISTANT FLOOR GRAPHIC FOR LOW TO MID-TRAFFIC AREAS (UP TO 6 MONTHS)

For more information, performance and warranty guide lines please contact your local Drytac office.

© 2018 Drytac Corporation. E&OE. All other trademarks are the property of their respective owners.

## TECHNICAL SPECIFICATION

### PRODUCT STRUCTURE

<b>Film</b>	Matte Pebble Textured Monomeric Soft Calendared PVC
<b>Adhesive</b>	Acrylic (Pressure Sensitive)
<b>Release Liner</b>	2 Side PE Coated, 1 Side Siliconised Kraft

### PRODUCT CHARACTERISTIC

<b>Film Thickness</b>	4 mil (100µ)	5 mil (125µ)
<b>Adhesive Layer</b>	1 mil (25µ)	
<b>Film/Adhesive Ratio</b>	4:1	
<b>UV Protection Factor</b>	Film and adhesive contain UV stabilizers, which prevent film degradation and provide UV protection to the underlying image	
<b>Outdoor Durability</b>	3 Years	
<b>Fire Rating</b>	Class 0	
<b>Application Temperature</b>	>41°F (20°C)	
<b>Service Temperature Range</b>	-4°F to 203°F (-20°C to 95°C)	
<b>Peel Strength (20 min, FTM1)</b>	11 N/25mm	
<b>Shelf Life</b>	1 year	
<b>Storage Conditions</b>	59°F to 72°F (15°C to 22°C); 50 - 55% Relative Humidity	

### PROCESS SETTINGS

Equipment Type & Temperature	Speed
<b>Roller Laminator</b> Room temperature to 104°F (40°C)	1 ft to 8 ft (0.3m to 2.5m) per minute
<b>Press</b>	Not recommended

**DRYTAC®**  
ADHESIVE SCIENCE

#### Europe

Filwood Road,  
Fishponds,  
Bristol, BS16 3RY,  
United Kingdom  
[bristol@drytac.com](mailto:bristol@drytac.com)  
Tel: +44 (0) 117 958 6500

#### Canada

105 Nuggett Court,  
Brampton,  
Ontario, L6T 5A9,  
Canada  
[toronto@drytac.com](mailto:toronto@drytac.com)  
Tel: +1 800.353.2883

#### USA

5601 Eastport Boulevard,  
Richmond,  
Virginia, 23231,  
USA  
[customerservice@drytac.com](mailto:customerservice@drytac.com)  
Tel: +1 800.280.6013