

Dusted Dryapply ASLAN EL 200



Glass decoration film with dusted effect for dry applications

The self-adhesive glass decoration film with dusted effect is ideal for creative effects on all glass surfaces.

The ASLAN Dryapply technology guarantees an easy application. Finest air release channels allow air bubbles to be wiped out with ease and make the application fast and easy.

For additional information please contact our technical advisory service:
+49 (0) 22 04. 7 08-80

Construction

face-film:	PVC (polymeric softened)	
thickness:	~ 80 µm	
adhesive:	acrylic pressure adhesive	square quantity: ~ 25 g/m ²
release liner:	silicone cardboard PE-coated on both sides	square weight: ~ 135 g/m ²

Characteristics

adhesive strength: (ASTMD-903)	immediately after 1 week	~ 3 N/25 mm ~ 9 N/25 mm
dimensional stability:	applied onto aluminum after 48 hours stored at 70 °C (25 x 25 cm)	max. -0.45 %
chemical resistance:	In a preece test of 24 hours the applied film is resistant to most petroleum based oils, greases and aliphatic solvents, mild acids, alkalis and salts.	
light proofness:	DIN 53 388	non-fade grade: 7-8 (Woll-Scale)
light transmission:	DIN 53 147	~ 97%
combustibility:	flame resistant (class B – s1, d0) according to DIN EN 13501	
temperature:	application temperature: service temperature range:	min. 15°C -30 °C up to +80 °C
durability:	up to 7 years outdoors, with vertical exposure, in central-European climate.	

ASLAN, Schwarz GmbH & Co. KG

Oberauel 2 · 51491 Overath · Germany

phone +49 (0) 2204. 708 80 · fax +49 (0) 2204. 708 50

e-mail info@ASLAN-Schwarz.com



www.ASLAN-Schwarz.com

ASLAN®

EXPERTISE IN SELF-ADHESIVE FILMS

Dusted Dryapply ASLAN EL 200



Processing

application:

Dry application only

For the application of letterings etc. we recommend our ASLAN application tapes respectively the ASLAN TMO.

It must always be ensured that no water accumulates at the cut edges of the film (e.g. in metal or plastic frameworks) and to prevent condensation on the adhered glass. In these cases as well as in the application on freestanding, outdoor glass surfaces, a white reaction of the adhesive can be caused.

storage life:

Before application the films can be stored for minimum 3 years from date of production. The film must be stored at room temperature (15-25 °C) and a relative humidity of the air of 50-60%. To avoid pressure points appearing on the roll surface, we recommend the rolls be stored either vertical standing or for this purpose designed 'hanging' racks.

State: 10|2013

All technical data and advice is based on our experience and measured testing that we believe to be reliable. It remains the customer's responsibility to test the suitability of our products for the intended purpose.

The quality of our products is regularly examined, upgraded and developed. We take the right, without prior notice, to adjust, upgrade and improve the chemical structures or physical characteristics of our products in accordance with our latest knowledge.

ASLAN, Schwarz GmbH & Co. KG

Oberauel 2 · 51491 Overath · Germany

phone +49(0)2204.708 80 · fax +49(0)2204.708 50

e-mail info@ASLAN-Schwarz.com



www.ASLAN-Schwarz.com

ASLAN The ASLAN logo consists of the word "ASLAN" in a bold, sans-serif font, followed by a red circle with a white crescent shape inside it.

EXPERTISE IN SELF-ADHESIVE FILMS