## Milky Dryapply ASLAN EL 210



## The glass decoration film with milk glass effect for dry applications

The self-adhesive glass decoration film with milk glass effect is ideal for creative effects on all glass surfaces. The ASLAN Dryapply technology guarantees an easy application. Finest air release channels allow air bubbles to be wiped out with ease and make the application fast and easy.

For additional information please contact our technical advisory service:

+49 (0) 22 04. 7 08-80

#### Construction

face-film: PVC

(polymeric softened)

thickness: ~ 80 µm

adhesive: acrylic pressure adhesive square quantity: ~ 25 g/m²

release liner: silicone cardboard

PE-coated on both sides square weight: ~ 135 g/m<sup>2</sup>

#### Characteristics

adhesive strength: immediately ~ 3 N/25 mm (ASTMD-903) after 1 week ~ 9 N/25 mm

dimensional stability: applied onto aluminum

after 48 hours stored at 70 °C

(25 x 25 cm) max. -0.45 %

chemical resistance: In a preece test of 24 hours the applied film is resistant to most petroleum based oils, greases and

aliphatic solvents, mild acids, alkalis and salts.

light proofness: DIN 53 388 non-fade grade: 7-8

(Woll-Scale)

light transmission: DIN 53 147 ~46%

combustibility: flame resistant (class B – s1, d0) according to DIN EN 13501

temperature: application temperature: min. 15°C

service temperature range: -30 °C up to +80 °C

 $\label{eq:durability:} \text{up to 7 years outdoors, with vertical exposure, in central-European climate.}$ 

ASLAN, Schwarz GmbH & Co. KG

Oberauel 2 · 51491 Overath · Germany **phone** +49 (0) 22 04. 7 08 80 · **fax** +49 (0) 22 04. 7 08 50 **e-mail** info@ASLAN-Schwarz.com









# Milky Dryapply ASLAN EL 210



## Processing

storage life:

application: Dry application only

For the application of letterings etc. we recommend our ASLAN application tapes respectively the ASLAN TMO.

It must always be ensured that no water accumulates at the cut edges of the film (e.g. in metal or plastic frameworks) and to prevent condensation on the adhered glass. In these cases as well as in the application on freestanding, outdoor glass surfaces, a white reaction of the adhesive can be caused.

Before application the films can be stored for minimum 3 years from date of production. The film must be stored at room temperature  $\{15-25\ ^{\circ}C\}$  and a relative humidity of the air of 50-60%. To avoid pressure points appearing on the roll surface, we recommend the rolls be stored either vertical standing or for this purpose designed `hanging´ racks.

State: 09|2018

All technical data and advice is based on our experience and measured testing that we believe to be reliable. It remains the customer's responsibility to test the suitability of our products for the intended purpose.

The quality of our products is regularly examined, upgraded and developed. We take the right, without prior notice, to adjust, upgrade and improve the chemical structures or physical characteristics of our products in accordance with our latest knowledge.

ASLAN, Schwarz GmbH & Co. KG

Oberauel 2 · 51491 Overath · Germany **phone** +49(0)2204.708 80 · **fax** +49(0)2204.708 50 **e-mail** info@ASLAN-Schwarz.com







